

# 99 Octane Unleaded Petrol

**Date of sampling: 19.12.2017**

**Samples taken by: independent inspectors**

TEST	UNIT	METHOD	RESULT
Appearance		Visual	Clear & bright
RON		IP 237	99.0
MON		IP 236	87.7
Density at 15°C	kg/m <sup>3</sup>	IP 365	754.6
Lead	mg/l	IP 428	< 2.5
Sulphur content	mg/kg	IP 490	6.9
Copper corrosion 3 hrs at 50°C		IP 154	1a
Benzene	% (v/v)	IP 429	0.3
M.T.B.E	% (v/v)	IP 466	5.0
E.T.B.E	% (v/v)	IP 466	< 0.2
Methanol	% (v/v)	IP 466	< 0.2
Ethanol	% (v/v)	IP 466	5.0
Iso-Propanol	% (v/v)	IP 466	< 0.2
Sec-Butanol	% (v/v)	IP 466	< 0.2
T.A.M.E	% (v/v)	IP 466	< 0.2
Tert-Butanol	% (v/v)	IP 466	< 0.2
Iso-Butanol	% (v/v)	IP 466	< 0.2
Oxygen content	% (m/m)	IP 466	2.70
Vapour pressure	kPa	IP 394	77.4
I.B.P	°C	EN ISO 3405	28.6
10% v rec. at	°C	EN ISO 3405	47.1
50% v rec. at	°C	EN ISO 3405	101.0
90% v rec. at	°C	EN ISO 3405	147.1
F.B.P	°C	EN ISO 3405	181.6
% v evap. at 70°C	% (v/v)	EN ISO 3405	34.8
% v evap. at 100°C	% (v/v)	EN ISO 3405	49.4
% v evap. at 150°C	% (v/v)	EN ISO 3405	91.2
Residue	% (v/v)	EN ISO 3405	1.0
Aromatics	% (v/v)	IP 156	33.1
Olefins	% (v/v)	IP 156	5.1