

Unleaded Petrol

Date of sampling: 31.10.2017

Samples taken by: independent inspectors

TEST	UNIT	METHOD	RESULT
Appearance		Visual	Clear & bright
RON		IP 237	95.4
MON		IP 236	85.1
Density at 15°C	kg/m ³	IP 365	720.9
Lead	mg/l	IP 428	< 2.5
Sulphur content	mg/kg	IP 490	4.9
Copper corrosion 3 hrs at 50°C		IP 154	1a
Benzene	% (v/v)	IP 429	0.7
M.T.B.E	% (v/v)	IP 466	< 0.2
E.T.B.E	% (v/v)	IP 466	< 0.2
Methanol	% (v/v)	IP 466	1.4
Ethanol	% (v/v)	IP 466	5.0
Iso-Propanol	% (v/v)	IP 466	< 0.2
Sec-Butanol	% (v/v)	IP 466	< 0.2
T.A.M.E	% (v/v)	IP 466	< 0.2
Tert-Butanol	% (v/v)	IP 466	< 0.2
Iso-Butanol	% (v/v)	IP 466	< 0.2
Oxygen content	% (m/m)	IP 466	2.67
Vapour pressure	kPa	IP 394	95.3
I.B.P	°C	EN ISO 3405	26.2
10% v rec. at	°C	EN ISO 3405	40.3
50% v rec. at	°C	EN ISO 3405	76.8
90% v rec. at	°C	EN ISO 3405	149.9
F.B.P	°C	EN ISO 3405	192.1
% v evap. at 70°C	% (v/v)	EN ISO 3405	47.0
% v evap. at 100°C	% (v/v)	EN ISO 3405	65.1
% v evap. at 150°C	% (v/v)	EN ISO 3405	90.0
Aromatics	% (v/v)	IP 156	18.8
Olefins	% (v/v)	IP 156	10.4